

## Half Coupling Link 8-054

### Product information



- Proof Load tested at 2.5 times the WLL with certification for each batch manufactured.
- Fatigue rated to 20,000 cycles at 1.5 times the WLL.
- Magnaflux crack detection is performed 100% on each batch.
- To combine with 8-088N Insulated Blank Swivel

**Material:** Quenched and Tempered Alloy Steel.

**Marking:** According to standard

**Temperature range:** Tempering temperature minimum 400°C

**Standard:** EN 1677-1

**Safety factor:** 4:1

**Grade:** 8

Part code	WLL ton	A mm	D mm	K mm	L mm	Weight kg	Delivery time
401200200140	2	18	9	22	28	0.1	10
401200320140	3.15	25	11	26	34	0.2	10
401200530140	5.3	30	16	35	45	0.4	10
401200800140	8	36	19	38	50	0.6	10
401201250140	12.5	42	22	46	60	1.1	10

## Blueprint

